

BlackhawkTM 5159 Asphalt Cutback

SELECTION & SPECIFICATION DATA

| | |
|---------------------------------|--|
| Type | Fast Drying Asphalt Cutback |
| Description | Blackhawk 5159 Asphalt Cutback coating is used for many metal corrosion and weather protection. Its high solids content gives it excellent coverage on marginally prepared metal and pavement surfaces, and it can also function as a primer for additional bituminous coatings. |
| Uses | <ul style="list-style-type: none">• Pavement coating• Corrosion protection coating on steel substrates• Primer for metal substrates |
| Color | Black |
| Primer | Self-priming |
| Topcoats | Consult Armor |
| Finish | Gloss |
| Dry Film Thickness (DFT) | 3 - 5 mils |
| Solids Content | 59% ± 2% by weight |
| VOC Value(s) | <450g/L (3.75 lbs/gal) |

SUBSTRATES & SURFACE PREPARATION

| | |
|------------|--|
| All | All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate. |
|------------|--|

MIXING & THINNING

| | |
|-----------------|---------------------|
| Mixing | No mixing necessary |
| Thinning | Do not thin |
| Cleanup | Mineral spirits |

APPLICATION GUIDANCE

| | |
|--|---|
| Airless Spray Single Leg or Pot | Pump size: 15:1 or greater Hose length: 20 ft x 1/2-inch ID |
| Brush | Apply with a wide fiber brush in order to create a smooth uniform film. |
| Roller | Use a low nap phenolic core roller. |

PACKAGING, ESTIMATING & HANDLING

| ITEM# | PACKAGING |
|-------------------|--------------------|
| K-5159-000-001 | Bulk - gallon |
| K-5159-005-001 | Pail - 4.7 gallons |
| K-5159-053-001-UN | Drum - 53 gallons |
| K-5159-275-001 | Tote - 270 gallons |

Theoretical Coverage Rate 220 square feet per gallon at 4 mils DFT.

Storage & Shelf Life Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). Store indoors. This product is not affected by excursions below these published storage temperatures, down to 10°F (-12°C), for a duration of no more than 14 days. Always inspect the product prior to use.

SAFETY

Safety Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.

TYPICAL PHYSICAL PROPERTIES

| | |
|----------------------------------|---------------|
| Viscosity, at 77°F (25°C) | 75 cps |
| Specific gravity, at 60°F (16°C) | 26.2 |
| Density, at 60°F (16°C) | 7.472 lbs/gal |

Rev. 05/2026

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see armor-inc.com.