

Tufchem™ II Joint Sealant

SELECTION & SPECIFICATION DATA

Type Urethane asphalt joint sealant

DescriptionTufchem II Joint Sealant is a black non-sag, 2-component flexible urethane asphalt joint

sealant.

• Vertical and horizontal expansion joints

· Concrete and metal surfaces

Features • Chemical resistant

Good elongation and recovery

Easy to mix

· High bond strength

Limitations •

• Not suitable for heavy traffic areas.

• Limited resistance to ultraviolet light

 Not for use beyond its chemical resistance or thermal capabilities. Consult Armor with specific questions.

INSTALLATION GUIDANCE

Reference Specifications CES-334 Tufchem II Membrane Installation

Specification

CES-130 Installation Specification for Armor Joint

Sealants

Installation Conditions Tufchem II Joint Sealant is formulated for ideal handling at 70°F (21°C). Materials and substrate should be acclimated to the air temperature prior to installation, and the air temperature should be between 50°F (10°C) and 90°F (32°C) during installation and cure. Bonding surfaces

must be clean, dry and neutral pH.

Ratio 45.0 base: 1.0 hardener

Mix Part A base for 1 minute. Slowly add Part B

Urethane Asphalt Hardener to Part A. Mix thoroughly for 3 full minutes. Do not mix partial

kits.

Consult Armor specification CES-334 titled Tufchem II Membrane Installation Specification,

section 7.0 for comprehensive mixing

instructions.

Work Life 45-60 minutes at 70°F (21°C)

Work life is shorter at higher temperatures.

Cleanup Mineral spirits

CURE TIME

TemperatureTack FreeFull Cure70°F (21°C)2-4 hours72 hours

<u>SAFETY</u>

Safety Mixes and applications of this product present a

number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data

sheets before using.

Ventilation Provide thorough air circulation during and after

application until the material has cured when

used in enclosed areas.



Tufchem™ II Joint Sealant

PACKAGING & ESTIMATING

Product	Code	Packaging
Tufchem II Joint Sealant Kit	29570	1.5-gallon kit

A 1.5-gallon kit consists of 1 x 12.8 lb pail of Part A base and 1 x 130 gm bottle of Part B hardener.

Theoretical Coverage

 $1/4 \times \frac{1}{2}$ -inch - 232 lineal feet (70.7 m) per unit $1/2 \times 1$ -inch - 58 lineal feet (17.6 m) per unit

Storage & Shelf Life Maintain products in original packaging and sealed until ready for use. Estimated shelf life for the Part A base and Part B hardener is 3 years when stored in a dry area at 70°F (21°C).

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with Armor.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	Black
Consistency	Non-sag
Density, ASTM C138	8.5 lb/gal (1,020 kg/m³)
Cured hardness, Shore A	30-40
Tensile strength, ASTM D412	>120 psi (1.5 MPa)
Elongation, ASTM D412	>100%
Adhesion to concrete, ASTM C321	Exceeds tensile strength of Tufchem II Joint Sealant
Adhesion to steel, ASTM D412	>120 psi (1.5 MPa)
Primer for concrete	Penntrowel™ Epoxy Primer or Novocoat™ SC1100 Concrete Primer

Rev 11/2025

TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see armor-inc.com.